



DNS® premium

Технические характеристики:		DNS® premium																						
		60		70		80		90		100		120		135		160		200		250		300		
Вес 1 кв.м.	g/m <sup>2</sup>	ISO 536	60	± 2.5	70	± 2.5	80	± 3.0	90	± 3.5	100	± 4.0	120	± 4.0	135	± 4.0	160	± 6.0	200	± 6.0	250	± 6.0	300	± 8.0
Толщина	mm/ 1000	ISO 534	85	± 4	96	± 3	107	± 3	119	± 3	131	± 4	153	± 4	173	± 4	202	± 5	271	± 6	333	± 6	400	± 8
Объемный вес	cm <sup>3</sup> /g		1.4		1.4		1.3		1.3		1.3		1.3		1.3		1.3		1.4		1.3		1.3	
Жесткость L&W в прод.направлении	MD	ISO 2493	min 55		min 80		min 125		min 160		min 190		min 280		min 400		min 600		min 1100		min 1900		min 2600	
Жесткость L&W в попер.направлении	CD	ISO 2493	min 28		min 35		min 58		min 70		min 100		min 280		min 400		min 600		min 600		min 1000		min 1500	
Щероховатость по Бендтсону		ISO 8791-2	200	± 50	140	± 50	140	± 50	140	± 50	140	± 50	140	± 50	140	± 50	140	± 50	140	± 50	140	± 50	140	± 50
Непрозрачность	%	ISO 2471	min 87.0		min 90.5		min 92.5		min 93.5		min 95.0		min 96.0		min 97.0		min 97.5		min 99.0		min 99.0		min 99.0	
Влажность	%	ISO 287	4.6	± 0.6	4.6	± 0.6	4.6	± 0.6	4.6	± 0.6	4.6	± 0.6	4.6	± 0.6	4.6	± 0.6	4.6	± 0.6	5.0	± 0.5	5.0	± 0.6	5.0	± 0.6
Беззна +UV	D65	ISO 2470	113.5	± 1.5	113.5	± 1.5	113.5	± 1.5	113.5	± 1.5	113.5	± 1.5	113.5	± 1.5	113.5	± 1.5	113.5	± 1.5	113.5	± 1.5	113.5	± 1.5	113.5	± 1.5
Визуальная безизна CIE		ISO 11475	169	± 3.0	169	± 3.0	169	± 3.0	169	± 3.0	169	± 3.0	169	± 3.0	169	± 3.0	169	± 3.0	169	± 3.0	169	± 3.0	169	± 3.0

Product meets ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, 14001 and 18001.

TECHNICAL CUSTOMER SERVICE SIGNIFICANCE OF VALUES: 2 SIGMA 16.11.2009

